

TECHNICAL INFORMATION

General Data

Metal effect type (Flame Retardant)
 Permanent & yellow adhesive
 Single side PE coated release paper (Air-free)

Applications

MDF
 Veneer
 Stainless steel
 Aluminum
 Iron, painted board
 Calcium silicate board
 PC
 Acryl
 PE,PP
 Melamine - baked steel board

Roll Sizes

122cm (48in) X 50M (164ft.)/Roll

Primer

Newmor marine water based primer -
 for porous surfaces such as MDF prior to
 wrapping. Application rate - 3 parts water,
 1 part primer
 Newmor solvent based primer - for use on
 the edges, overlaps and hard surfaces such as
 laminate.
 For more information, please enquire.

Shelf Life

Shelf life is 2 years from the date of
 production.
 Storage condition : This product has to
 be kept away from high temp., humidity
 and direct sunlight.
 (Recommended storage condition:
 20°C×50% R.H)

Installation Guide:

It is recommended to use the Primer
 provided by Newmor when installing.
 The ambient temperature should be
 maintained at 15 to 25 ° C for 72 hours
 prior to application, and for 48 hours
 during and after the installation. Please be
 careful to install the interior film in the same
 lot number to one space. There is a slight
 color tolerance in different lot number.
 Overlapping application method is required.

Fire Certifications

For more information on fire certifications,
 please contact us.

Physical Features

Item	Spec	Test Method
Thickness (without a release paper)	0.16~0.27mm	Micrometer
Tensile strength (kgf/cm²)	(L)150~350 / (W)100~300	ASTM D882
Elongation (%)	(L)0~400 / (W)0~400	ASTM D882
Adhesion (24hr)	≥ 1,000g/in	180 peeling PSTC-1
Application temp.	15~25°C	15 to 25°C optimum, on clean substrate
Thickness of a release paper	0.14mm ± 10%	Micrometer
Dimensional stability	0.8mm ↓	Adhered to Aluminum Plate, Length Direction (100°C Oven, 2hr , Average)

