

TECHNICAL INFORMATION

General Data

Solid type (Flame Retardant)
Permanent & yellow adhesive
Single side PE coated release paper (Air-free)

Applications

MDF
Veneer
Stainless steel
Aluminum
Iron, painted board
Calcium silicate board
PC
Acryl
PE,PP
Melamine - baked steel board

Roll Sizes

122cm (48in) X 50M (164ft.)/Roll

Primer

Newmor marine water based primer - for porous surfaces such as MDF prior to wrapping. Application rate - 3 parts water, 1 part primer
Newmor solvent based primer - for use on the edges, overlaps and hard surfaces such as laminate .
For more information, please enquire.

Shelf Life

Shelf life is 2 years from the date of production.
Storage condition : This product has to be kept away from high temp., humidity and direct sunlight.
(Recommended storage condition: 20°C×50% R.H)

Installation Guide:

It is recommended to use the Primer provided by Newmor when installing. The ambient temperature should be maintained at 15 to 25 ° C for 72 hours prior to application, and for 48 hours during and after the installation. Please be careful to install the interior film in the same lot number to one space. There is a slight color tolerance in different lot number. Overlapping application method is required.

Fire Certifications

For more information on fire certifications, please contact us.

Physical Features

Item	Spec	Test Method
Thickness (without a release paper)	0.15~0.26mm	Micrometer
Tensile strength (kgf/cm²)	(L)150~350 / (W)100~300	ASTM D882
Elongation (%)	(L)0~400 / (W)0~400	ASTM D882
Adhesion (24hr)	≥ 1,000g/in	180 peeling PSTC-1
Application temp.	15~25°C	15 to 25°C optimum, on clean substrate
Thickness of a release paper	0.14mm ± 10%	Micrometer
Dimensional stability	0.8mm ↓	Adhered to Aluminum Plate, Length Direction (100°C Oven, 2hr , Average)

